





**Purpose** To compare the mixing performance of the Xemex® Static Mixer with commercially available mixers.

**Experimental** The 2-part formulation was dispensed using Re Mixer’s automated cartridge dispenser, having preset flow rate and purge routines. After curing at room temperature for 48 hours, hardness was determined through a single-blind collection using Rex Gauge’s RX-DD Series Durometer, and in accordance with ASTM D2240.

# 3M™ Scotch-Weld® LSB60

## Cured Hardness



**Mixing Performance** The hardness data suggests that Xemex yielded the best mixing performance for 3M™ Scotch-Weld® LSB60 adhesive. With a retained volume of only 2.5 mL, Xemex outperformed mixers with 24 elements, which have retained volumes in the order of 5 to 10 mL. These results suggest that Xemex is a candidate for applications using LSB60.

**Back Pressure** From this data, one should expect back pressures with Xemex to be comparable to MCH 08-24T and slightly higher than MCQ 10-24T at equivalent flow rates.

Formulation	Type	Mix Ratio**	Mixed** (cP)	Part A**	Part B**	Worklife** (min)	Keywords
3M™ Scotch-Weld® LSB60	Epoxy	1:1	—	17,200	68,200	90	Filled
Laboratory Technician		Cured Time		Laboratory		Report Prepared by	
Lukas Duddleston, MS		48 hours		23±2 °C   35±5 % RH		Lukas Duddleston, MS	

\*\*As reported in 3M’s Technical Data Sheet

THE DATA AND INFORMATION CONTAINED ON THIS REPORT IS FOR INFORMATIONAL PURPOSES ONLY. RE MIXERS, INC. HEREBY DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES REGARDING THE PRODUCTS, TEST RESULTS, DATA, AND INFORMATION CONTAINED IN THIS REPORT (INCLUDING, WITHOUT LIMITATION, ANY WARRANTY OF MERCHANTABILITY, OR FITNESS FOR A PARTICULAR PURPOSE, OR INFRINGEMENT), WHETHER EXPRESS OR IMPLIED BY LAW, COURSE OF DEALING, COURSE OF PERFORMANCE, OR OTHERWISE. In addition, while the data and information contained herein is believed to be reliable, all such data and information is provided “as-is”, “with all faults”, and no warranty is expressed or implied regarding the reliability, accuracy or completeness of the data, or the results to be obtained from the use thereof. All recommendations or suggestions for use are made without guarantee and it is the user’s sole liability and responsibility to test and determine any listed product’s suitability for their own purpose and application. 3M™ and Scotch-Weld®, are trademarks of 3M Company. Re Mixers, Inc. is not associated with or sponsored by 3M Company. Any use of 3M™, Scotch-Weld®, or other third party trademarks are for informational and/or comparative fair use purposes only.